



ARA 630 60%in Xylene

Short_oil,alkyd resin based on soya fatty acid

Application

- | | | |
|---|-----------------|-------|
| • NC paint for wood and metal | Solids content% | 60± 2 |
| • High performance baking enamels(20-30min/140-160c). | Viscosity50 inX | T-U |
| • On layers and top coats for household appliance | Acid value | max10 |
| • (Blends with acrylic resins and cross linked with melamine) | Density g/cm3 | 1.00 |
| • Curing paints in combination with NC | color | Max4 |
| • Modifier resin in coil coating systems | oil length | 27% |

Principal properties

- Suitable flexibility,high gloss,high hardness
- Good adhesion,air drying
- High outdoor durability,chemical resistance
- High build and very good adhesion

Compatibility

With most short oil alkyd,Amino resins,Nitrocellulose,Ester plasticizers.
Limited compatible with many Medium,Long Oil and Acrylic Resins.

Solubility

White spirit:	In soluble
Butyl acetate:	Complete
MEK:	Complete
N-Butanol:	Complete
Toluene:	Complete

GSM

Website: www.goodrichkimya.com

Email: info@goodrichkimya.com

Adress: Fatih mah Atatürk Cd No:55/2 Gaziemir / İzmir

+90 552 608 0011

GSM: +90 530 707 54 91

+90 232 608 1111

+90 232 608 2222